

Diameter		Size Circ.	Weight			Breaking Load		
mm	Inches	Inches	Ktex	Kg/100m	lbs/100ft	Kgf	lbf	kN
24	1	3	261	26,1	17,5	8 056	17 760	79
26	1 1/32	3 1/4	306	30,6	20,6	9 279	20 457	91
28	1 1/8	3 1/2	355	35,5	23,9	10 707	23 605	105
30	1 1/4	3 3/4	408	40,8	27,4	12 135	26 752	119
32	1 5/16	4	464	46,4	31,2	13 664	30 124	134
34	1 11/32	4 1/4	525	52,5	35,3	15 194	33 496	149
36	1 1/2	4 1/2	587	58,7	39,4	16 825	37 093	165
38	1 9/16	4 3/4	656	65,6	44,1	18 559	40 915	182
40	1 5/8	5	725	72,5	48,7	20 292	44 736	199
44	1 3/4	5 1/2	877	87,7	58,9	23 963	52 829	235
48	2	6	1 040	104	69,9	28 144	62 046	276
52	2 1/8	6 1/2	1 220	122	82	32 631	71 938	320
56	2 1/4	7	1 420	142	95,4	37 220	82 054	365
60	2 1/2	7 1/2	1 630	163	109,5	42 114	92 845	413
64	2 5/8	8	1 860	186	125	47 111	103 860	462
68	2 3/4	8 1/2	2 100	210	141,1	52 821	116 450	518
72	2 7/8	9	2 350	235	157,9	58 634	129 263	575
80	3 1/4	10	2 900	290	194,9	70 871	156 240	695
90	3 9/16	11 1/8	3 750	375	252	91 673	202 101	899



- **Raw material: Mixed Polyolefin**
- **Specific Gravity: 0,93**
- **Melting Point: 165°C**
- **Elongation at % of BS:**

25% 6,0%

50% 11,5%