

Diameter		Size Circ.	Weight			Breaking Load		
mm	Inches	Inches	Ktex	Kg/100m	lbs/100ft	Kgf	lbf	kN
24	1	3	266	26,6	17,9	10 707	23 605	105
26	1 1/32	3 1/4	317	31,7	21,3	12 848	28 326	126
28	1 1/8	3 1/2	368	36,8	24,7	15 092	33 271	148
30	1 1/4	3 3/4	430	43,0	28,9	17 335	38 217	170
32	1 5/16	4	478	47,8	32,1	19 375	42 713	190
36	1 1/2	4 1/2	606	60,6	40,7	24 269	53 504	238
40	1 5/8	5	750	75	50,4	29 572	65 194	290
44	1 3/4	5 1/2	900	90	60,5	35 282	77 783	346
48	2	6	1 075	107,5	72,2	41 503	91 496	407
52	2 1/8	6 1/2	1 265	126,5	85	48 029	105 884	471
56	2 1/4	7	1 460	146	98,1	55 269	121 845	542
60	2 1/2	7 1/2	1 680	168	112,9	62 713	138 256	615
64	2 5/8	8	1 910	191	128,3	70 871	156 240	695
68	2 3/4	8 1/2	2 160	216	145,1	79 538	175 349	780



- **Raw material: Polyester / Mixed Polyolefins (HT)**
- **Specific Gravity: 0,99 (floats)**
- **Melting Point: 265°C / 165°C**
- **Elongation at % of BS:**

**25% .... 4,0%**

**50% .... 6,0%**