

Diameter		Size Circ.	Weight			Breaking Load		
mm	Inches	Inches	Ktex	Kg/100m	lbs/100ft	Kgf	lbf	kN
24	1	3	437	43,7	29,4	9 687	21 357	95
28	1 1/8	3 1/2	595	59,5	40	12 747	28 101	125
30	1 1/4	3 3/4	683	68,3	45,9	14 276	31 473	140
32	1 5/16	4	777	77,7	52,2	16 316	35 969	160
36	1 1/2	4 1/2	984	98,4	66,1	20 394	44 961	200
40	1 5/8	5	1 210	121	81,3	25 493	56 201	250
44	1 3/4	5 1/2	1 470	147	98,8	30 592	67 442	300
48	2	6	1 750	175	117,6	36 200	79 806	355
52	2 1/8	6 1/2	2 050	205	137,8	43 338	95 543	425
56	2 1/4	7	2 380	238	159,9	48 437	106 783	475
60	2 1/2	7 1/2	2 730	273	183,4	54 045	119 147	530
64	2 5/8	8	3 110	311	209	61 183	134 884	600
72	2 7/8	9	3 930	393	264,1	76 479	168 604	750



- **Raw material: Polyester (HT)**
- **Specific Gravity: 1,38 (sinks)**
- **Melting Point: 265°C**
- **Elongation at % of BS:**

**25% .... 5,0%**

**50% .... 8,0%**