

Diameter		Size Circ.	Weight			Breaking Load		
mm	Inches	Inches	Ktex	Kg/100m	lbs/100ft	Kgf	lbf	kN
24	1	3	261	26,1	17,5	10 605	23 380	104
26	1 1/32	3 1/4	306	30,6	20,6	12 339	27 202	121
28	1 1/8	3 1/2	355	35,5	23,9	14 174	31 248	139
30	1 1/4	3 3/4	408	40,8	27,4	16 112	35 519	158
32	1 5/16	4	464	46,4	31,2	18 253	40 240	179
36	1 1/2	4 1/2	587	58,7	39,4	22 842	50 357	224
40	1 5/8	5	725	72,5	48,7	27 940	61 597	274
44	1 3/4	5 1/2	877	87,7	58,9	33 345	73 512	327
48	2	6	1 040	104	69,9	39 259	86 550	385
52	2 1/8	6 1/2	1 220	122	82	45 683	100 713	448
56	2 1/4	7	1 420	142	95,4	52 414	115 550	514
60	2 1/2	7 1/2	1 630	163	109,5	59 450	131 062	583
64	2 5/8	8	1 860	186	125	66 996	147 698	657
68	2 3/4	8 1/2	2 100	210	141,1	75 153	165 682	737



- **Raw material: Mixed Polyolefin (HT)**
- **Specific Gravity: 0,94 (floats)**
- **Melting Point: 165°C**
- **Elongation at % of BS:**

**25% .... 2,8%**

**50% .... 5,5%**