

Varenr.	Diameter		Size Circ.	Weight			Breaking Load		
	mm	Inches	Inches	Ktex	Kg/100m	lbs/100ft	Kgf	lbf	kN
-									
SU0403SL	4	5/32	1/2	8	0,8	0,5	337	742	3,3
SU0503SL	5	3/16	5/8	12	1,2	0,8	510	1 124	5
SU0603SL	6	1/4	3/4	16	1,6	1,1	689	1 520	6,8
SU0803SL	8	5/16	1	29	2,9	1,9	1 193	2 630	11,7
SU1003SL	10	3/8	1 1/4	45	4,5	3	1 835	4 047	18
SU1203SL	12	1/2	1 1/2	65	6,5	4,4	2 590	5 710	25,4
SU1403SL	14	9/16	1 3/4	88	8,8	5,9	3 467	7 643	34
SU1603SL	16	5/8	2	116	11,6	7,8	4 436	9 779	43,5
SU1803SL	18	3/4	2 1/4	147	14,7	9,9	5 557	12 252	54,5
SU2003SL	20	13/16	2 1/2	181	18,1	12,2	6 751	14 882	66,2
SU2203SL	22	7/8	2 3/4	219	21,9	14,7	8 066	17 782	79,1
SU2403SL	24	1	3	261	26,1	17,5	9 463	20 862	92,8
SU2603SL	26	1 1/32	3 1/4	306	30,6	20,6	10 911	24 054	107
SU2803SL	28	1 1/8	3 1/2	355	35,5	23,9	12 543	27 651	123
SU3003SL	30	1 1/4	3 3/4	408	40,8	27,4	14 276	31 473	140
SU3203SL	32	1 5/16	4	464	46,4	31,2	16 010	35 295	157
SU3403SL	34	1 11/32	4 1/4	525	52,5	35,3	17 845	39 341	175
SU3603SL	36	1 1/2	4 1/2	587	58,7	39,4	19 783	43 612	194
SU3803SL	38	1 9/16	4 3/4	656	65,6	44,1	21 822	48 108	214
SU4003SL	40	1 5/8	5	725	72,5	48,7	23 861	52 605	234
SU4403SL	44	1 3/4	5 1/2	877	87,7	58,9	28 246	62 271	277
SU4803SL	48	2	6	1 040	104	69,9	33 141	73 062	325
SU5203SL	52	2 1/8	6 1/2	1 220	122	82	38 341	84 527	376
SU5603SL	56	2 1/4	7	1 420	142	95,4	43 746	96 442	429
SU6003SL	60	2 1/2	7 1/2	1 630	163	109,5	49 558	109 256	486
SU6403SL	64	2 5/8	8	1 860	186	125	55 473	122 294	544
SU6803SL	68	2 3/4	8 1/2	2 100	210	141,1	62 101	136 907	609
SU7203SL	72	2 7/8	9	2 350	235	157,9	69 035	152 194	677
SU8003SL	80	3 1/4	10	2 900	290	194,9	83 413	183 891	818
SU9003SL	90	3 9/16	11 1/8	3 750	375	252	107 886	237 845	1 058



- **Raw material: Mixed Polyolefin (HT)**
- **Specific Gravity: 0,94 (floats)**
- **Melting Point: 165°C**
- **Elongation at % of BS:**

**25% .... 6,0%**

**50% .... 11,5%**